



M A R T E K





INTERNATIONAL

depuis 1996

## BRECCIA ALBA



Compressive strenght	102.9 MPa
After freezing	
Flexural strenght	12.9 MPa
Porosity	1.14 %
Water absorption	0.29 %
Impact test	
Wear test	18.5 mm
Bulk density	2758 Kg / m3

 Quarry location :	Albany
 Availability :	Medium
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 - [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

