



M A R T E K





INTERNATIONAL

depuis 1996

BRECCIA AURORA



Compressive strenght	79 MPa
After freezing	
Flexural strenght	10.7 MPa
Porosity	
Water absorption	0.20 %
Impact test	
Wear test	
Bulk density	2700 Kg / m3

 Quarry location :	Italy
 Availability :	Limited
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 - contact@martek-international.com

- www.martek-international.com -

