



M A R T E K





INTERNATIONAL

depuis 1996

BRECCIA PERNICE



Compressive strenght	139 MPa
After freezing	
Flexural strenght	13.2 MPa
Porosity	2.12 %
Water absorption	0.5 %
Impact test	
Wear test	20.5 mm
Bulk density	2664 Kg / m3

 Quarry location :	Italy
 Availability :	Medium
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 - contact@martek-international.com

- www.martek-international.com -

