




M A R T E K





INTERNATIONAL

depuis 1996

BRECCIA SARRANCOLIN



Compressive strenght	91.9 MPa
After freezing	
Flexural strenght	11.4 MPa
Porosity	0.23 %
Water absorption	0.10 %
Impact test	
Wear test	24.7 mm
Bulk density	2710 Kg / m3

 Quarry location :	France
 Availability :	Limited
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

