



M A R T E K





INTERNATIONAL

depuis 1996

## ABSOLUTE BLACK



Compressive strength	219 MPa
After freezing	
Flexural strength	14.5 MPa
Porosity	0.20 %
Water absorption	0.08 %
Impact test	
Wear test	
Bulk density	2950 Kg / m <sup>3</sup>

 Quarry location :	India
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

**MARTEK International**

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

