




M A R T E K





INTERNATIONAL

depuis 1996

AZUL BAHIA



Compressive strenght	174.1 MPa
After freezing	142.6 MPa
Flexural strenght	16.2 MPa
Porosity	
Water absorption	0.22 %
Impact test	40 cm
Wear test	
Bulk density	2553 Kg / m3

 Quarry location :	Brazil
 Availability :	Limited
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Medium

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

