

M A R T E K





INTERNATIONAL

depuis 1996

BLANCO BERROCAL



Compressive strenght	175 MPa
After freezing	
Flexural strenght	13.6 MPa
Porosity	0.70 %
Water absorption	0.30 %
Impact test	61 cm
Wear test	15.7 mm
Bulk density	2630 Kg / m ³

 Quarry location :	Spain
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

