


M A R T E K





INTERNATIONAL

depuis 1996

G623



Compressive strenght	172.85 MPa
After freezing	
Flexural strenght	17.38 MPa
Porosity	
Water absorption	0.30 %
Impact test	
Wear test	
Bulk density	2610 Kg / m3

 Quarry location :	PRC
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

