


M A R T E K





INTERNATIONAL

depuis 1996

ZIMBABWE BLACK



Compressive strenght	190 MPa
After freezing	
Flexural strenght	23 MPa
Porosity	0.4 %
Water absorption	0.11 %
Impact test	
Wear test	
Bulk density	2930 Kg / m3

 Quarry location :	Zimbabwe
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Medium

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

