




M A R T E K





INTERNATIONAL

depuis 1996

AZUL BATEIG



Compressive strenght	83.9 MPa
After freezing	11.9 MPa
Flexural strenght	4 MPa
Porosity	13.5 %
Water absorption	4.9 %
Impact test	
Wear test	25.3 mm
Bulk density	2270 Kg / m3

 Quarry location :	Spain
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

