



M A R T E K





INTERNATIONAL

depuis 1996

BEIGE FINE



Compressive strength	74.5 MPa
After freezing	17.3 MPa
Flexural strength	MPa
Porosity	3.5 %
Water absorption	1.51 %
Impact test	
Wear test	4.2 mm
Bulk density	2327 Kg / m ³

 Quarry location :	Portugal
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

