



M A R T E K





INTERNATIONAL

depuis 1996

MOKA CREAM



Compressive strenght	90.9 MPa
After freezing	
Flexural strenght	19.2 MPa
Porosity	5.9 %
Water absorption	2.34 %
Impact test	40 cm
Wear test	4 mm
Bulk density	2315 Kg / m3

 Quarry location :	Portugal
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

