



M A R T E K





INTERNATIONAL

depuis 1996

PIERRE DE VERS



Compressive strenght	10 MPa
After freezing	
Flexural strenght	2.8 MPa
Porosity	28 %
Water absorption	
Impact test	
Wear test	40.5 mm
Bulk density	1950 Kg / m3

 Quarry location :	France
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

