



M A R T E K





INTERNATIONAL

depuis 1996

PIETRA SERENA



Compressive strenght	114.5 MPa
After freezing	101.7 MPa
Flexural strenght	17 MPa
Porosity	
Water absorption	0.06 %
Impact test	
Wear test	7.1 mm
Bulk density	2560 Kg / m3

 Quarry location :	Italy
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

