



M A R T E K





INTERNATIONAL

depuis 1996

PIETRA DI VICENZA



Compressive strenght	40.8 MPa
After freezing	
Flexural strenght	25.9 MPa
Porosity	
Water absorption	7.49 %
Impact test	
Wear test	0.47 mm
Bulk density	2210 Kg / m3

 Quarry location :	Italy
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

