



M A R T E K





INTERNATIONAL

depuis 1996

TRANI GOLD



Compressive strenght	175 MPa
After freezing	163.8 MPa
Flexural strenght	18.1 MPa
Porosity	0.01 %
Water absorption	0.11 %
Impact test	
Wear test	2.79 mm
Bulk density	2720 Kg / m3

 Quarry location :	Italy
 Availability :	Medium/Large
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

