



M A R T E K





INTERNATIONAL

depuis 1996

BIANCO CARRARA C



Compressive strenght	130.8 MPa
After freezing	127.5 MPa
Flexural strenght	19.8 MPa
Porosity	
Water absorption	0.11 %
Impact test	56 cm
Wear test	0.58 mm
Bulk density	2711 Kg / m3

 Quarry location :	Italy
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

