



M A R T E K





INTERNATIONAL

depuis 1996

## BIANCO THASSOS



Compressive strenght	109.3 MPa
After freezing	93.6 MPa
Flexural strenght	15.2 MPa
Porosity	
Water absorption	
Impact test	
Wear test	5.90 mm
Bulk density	2860 Kg / m3

 Quarry location :	Greece
 Availability :	Medium
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

**MARTEK International**

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

