



M A R T E K





INTERNATIONAL

depuis 1996

## BOTTICINO CLASSICO



Compressive strenght	211.9 MPa
After freezing	204.2 MPa
Flexural strenght	12.7 MPa
Porosity	
Water absorption	0.14 %
Impact test	29 cm
Wear test	0.67 mm
Bulk density	2710 Kg / m3

 Quarry location :	Italy
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

**MARTEK International**

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

