



M A R T E K

INTERNATIONAL





depuis 1996

## BOTTICINO FIORITO

---



Compressive strenght	199 MPa
After freezing	
Flexural strenght	13.9 MPa
Porosity	
Water absorption	0.3 %
Impact test	37 cm
Wear test	
Bulk density	2710 Kg / m3

 Quarry location :	Italy
 Availability :	Good
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

**MARTEK International**

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

