



M A R T E K





INTERNATIONAL

depuis 1996

CALACATTA CLASSICO



Compressive strenght	121.1 MPa
After freezing	111.3 MPa
Flexural strenght	19 MPa
Porosity	
Water absorption	0.23 %
Impact test	48 cm
Wear test	
Bulk density	2698 Kg / m3

 Quarry location :	Italy
 Availability :	Medium
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

