




M A R T E K





INTERNATIONAL

depuis 1996

IRISH GREEN



Compressive strenght	100.7 MPa
After freezing	
Flexural strenght	8.10 MPa
Porosity	
Water absorption	0.60 %
Impact test	
Wear test	
Bulk density	2600 Kg / m3

 Quarry location :	Ireland
 Availability :	Medium
 Block size dimensions :	Medium
 Rate of change slab/photo :	Medium

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

