



M A R T E K





INTERNATIONAL

depuis 1996

NERO MARQUINA



Compressive strenght	61.7 MPa
After freezing	50.2 MPa
Flexural strenght	13.4 MPa
Porosity	
Water absorption	0.17 %
Impact test	38 cm
Wear test	
Bulk density	2690 Kg / m3

 Quarry location :	Spain
 Availability :	Good
 Block size dimensions :	Medium/Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

