



M A R T E K





INTERNATIONAL

depuis 1996

RUIVINA DARK



| | |
|----------------------|--------------|
| Compressive strenght | 86.3 MPa |
| After freezing | |
| Flexural strenght | 14 MPa |
| Porosity | 0.30 % |
| Water absorption | 0.10 % |
| Impact test | |
| Wear test | 2 mm |
| Bulk density | 2700 Kg / m3 |

| | |
|---|--------------|
|  Quarry location : | Portugal |
|  Availability : | Good |
|  Block size dimensions : | Medium/Large |
|  Rate of change slab/photo : | Limited |

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 - contact@martek-international.com

- www.martek-international.com -

