




M A R T E K





INTERNATIONAL

depuis 1996

SAHARA NOIR



Compressive strenght	72.1 MPa
After freezing	
Flexural strenght	11.8 MPa
Porosity	
Water absorption	0.92 %
Impact test	43 cm
Wear test	
Bulk density	2720 Kg / m3

 Quarry location :	Tunisia
 Availability :	Medium/Large
 Block size dimensions :	Large
 Rate of change slab/photo :	Limited

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

