

M A R T E K





INTERNATIONAL

depuis 1996

## STATUARIETTO



Compressive strenght	130.8 MPa
After freezing	127.5 MPa
Flexural strenght	19.8 MPa
Porosity	
Water absorption	0.11 %
Impact test	56 cm
Wear test	0.58 mm
Bulk density	2711 Kg / m3

 Quarry location :	Italy
 Availability :	Limited
 Block size dimensions :	Medium
 Rate of change slab/photo :	Limited

**MARTEK International**

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – [contact@martek-international.com](mailto:contact@martek-international.com)

- [www.martek-international.com](http://www.martek-international.com) -

