

M A R T E K





INTERNATIONAL

depuis 1996

ONYX GREEN



| | |
|----------------------|--------------|
| Compressive strenght | 92 MPa |
| After freezing | |
| Flexural strenght | 12.26 MPa |
| Porosity | |
| Water absorption | 1.30 % |
| Impact test | |
| Wear test | |
| Bulk density | 2400 Kg / m3 |

| | |
|---|--------------|
|  Quarry location : | Iran |
|  Availability : | Limited |
|  Block size dimensions : | Small/Medium |
|  Rate of change slab/photo : | Medium |

MARTEK International

- T : (33)04 91 46 70 01 - M : (33)06 73 76 29 46 – contact@martek-international.com

- www.martek-international.com -

